

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : D21G 1/00, D21H 19/00		A1	(11) International Publication Number: WO 99/67462
			(43) International Publication Date: 29 December 1999 (29.12.99)
(21) International Application Number: PCT/FI99/00563		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).	
(22) International Filing Date: 24 June 1999 (24.06.99)		Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>	
(30) Priority Data: 981467 25 June 1998 (25.06.98) FI			
(71) Applicant (for all designated States except US): VALMET CORPORATION [FI/FI]; Panuntie 6, FIN-00620 Helsinki (FI).			
(72) Inventors; and (75) Inventors/Applicants (for US only): KYTÖNEN, Pauli [FI/FI]; Kuikantie 3, FIN-04320 Riihikallio (FI). TANI, Mikko [FI/FI]; Mikkolantie 4 C 11, FIN-04300 Tuusula (FI).			
(74) Agent: SEPPÖ LAINE OY; Itämerenkatu 3 B, FIN-00180 Helsinki (FI).			
(54) Title: METHOD AND ARRANGEMENT FOR CALENDERING PAPER AND BOARD BEFORE AND AFTER COATING			
(57) Abstract <p>A method for calendering paper or board in the manufacture of coated grades of paper or board. According to the method, at least one of the surfaces of an uncoated base material web is calendered, at least one layer of coating mix being applied onto said surface, and at least the coated surface of the base web is calendered again. The uncoated surface of the base web is calendered by means of a shoe calender having a nip length of at least 50 mm, and the coated surface of the base web is calendered by means of a calender having a nip length of 50 mm at the most.</p>			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Moongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NZ	New Zealand	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Method and arrangement for calendering paper and board before and after coating.

5 The present invention concerns a method according to the preamble of claim 1 for calendering paper and board in the manufacture of coated grades of paper or board.

The invention also concerns an arrangement for implementing the method.

10 Paper or board is calendered in order to improve its printability properties. Calendering increases the smoothness and glare of the surface, and in addition, it affects the thickness and bulk (cm^3/g) of the material. Changes other than
15 those affecting the surface are usually unintentional, because changes in material thickness are not desired. The unavoidable change in bulk must be adapted to the desired surface quality such that the desired surface quality and bulk as well as the desired final material thickness are
20 obtained. Uncoated material can be subjected to calendering prior to the coating step, or the calendering may be carried out after coating, or at several steps. Many types of calendering methods and apparatuses are available, whereof machine calenders, softcalenders and supercalenders may be
25 mentioned, and as the most recent type of calenders, shoe calenders and belt calenders may be cited. Each type of calender has its individual effect on the quality of the produced material, as well as its own typical field of application. The different types of calenders and their use
30 are well known in the manufacture of paper and board.

European patent No. 0 370 185 describes a typical shoe calender comprising a backing roll and an arched shoe-like stop designed to encircle part of the roll surface. An
35 endless belt travels round the shoe and is fitted to move at

the same speed as the material being treated. The material to be calendered travels between the belt and the backing roll and is glazed against the surface of the backing roll. The backing roll can be heated and deformations of the surface occur due to the press power of the shoe and the backing roll, and due to heat. The glazing result is naturally also affected by the wetness of the web. The shoe calender provides a number of advantages, such as the fact that, due to the longer dwell time, a smaller compression load and possibly temperature may be used than in roll calenders, still achieving a similar end result. Due to the reduced nip pressure a smaller contraction of the calendered web is achieved, thus preserving a greater part of the original stiffness, or bulk, of the web.

A shoe calender usually provides better glare than the corresponding softcalender.

The German Published Application DE 43 22 876 describes a shoe calender with a smaller shoe width and thus also a shorter glazing zone than in the above-cited solution. In this calender, two calendering nips can be fitted against the same backing roll, and the strap surrounding the shoe is similar to the roll jacket. In DE publication No. 44 10 129, a shoe calender is described where the shoe is divided into two zones in the moving direction of the web being treated, the press power of the zones against the backing roll being adjustable independent of each other.

Belt calenders, in which the calender zone is provided by a roll and a belt pressed against said roll by means of a second roll, bear a close resemblance to shoe calenders. The belt may be flexible in the direction of its thickness, whereby a pressure treatment zone defined by the properties of the belt and the geometry and loading force of the

calender rolls used will be provided between the backing roll and the belt. Also a calender having a very short pressing shoe is termed a belt calender, whereby the length of the nip almost corresponds to a nip formed with two rolls.

5

Long-nip calenders, belt calenders and softcalenders are well suited for calendering board. In WO 96/28609, a coated packing board is described, whose manufacturing process involves the use of a lengthened soft calender nip. The board is calendered after coating. By calendering, a sufficiently good printing surface is obtained, and due to the lengthened nip, a lower pressure may be applied during calendering, whereby a smaller reduction in density and basis weight is achieved. This is of particular advantage in the manufacture of packing board because a lighter board provides greater flexural strength. The length of the lengthened nip of the calender used is reported as being from 30 to 100 mm, preferably 60 to 70 mm. Thus, the calender used is still one having a fairly short nip. The web speed and dwell time used are not reported.

20

In WO 97/44524, a method for manufacturing LWC paper is described. This publication makes clear the considerable effect of the treatment temperature on the properties of the paper being manufactured. According to the publication, coated paper is calendered in a soft calender and the temperature of the paper is kept below the softening temperature of lignin. According to the publication, the method achieves much better glare than previously known methods involving the use of a softcalender.

25

30

The present invention aims at providing a method for manufacturing precalendered and end-calendered coated paper or board.

35

The invention is based on first calendering the material to be treated in a long-nip calender, and after coating, in a calender having a short nip.

5 In more detail, the method according to the invention is characterized by what is stated in the characterizing part of claim 1.

10 The arrangement according to the invention, then, is characterized by what is stated in the characterizing part of claim 6.

The invention achieves considerable benefits.

15 Paper and board which consist of plant fibres behave in different ways during calendering when uncoated and when coated. In addition, the calendering is essentially affected by the moisture content of the material, wherefore
20 calendering is usually accompanied by moisture control of the treated material. By means of the invention, these material properties can be exploited, thereby achieving paper and especially board having better printability and strength properties than previously. As regards board and also the
25 thickest grades of paper, a change in density during calendering essentially affects the strength properties of the material in the above-described manner, wherefore it is of particular advantage to be able to control the calendering process during the different manufacturing steps in
30 accordance with the material properties when producing these materials.

The invention is explained in more detail below with the aid of the following detailed description.

35 In the following, the solution of the invention is explained

in the context of board manufacture, which is what the invention is particularly well suited for. The invention is also applicable to a similar treatment of a paper web.

5 During calendering, the demands of the process vary according to whether the web being treated is coated or whether uncoated material is being treated. This is due to the different behaviour of the fibres constituting the material (usually fibres derived from wood), and the coat, by the
10 action of the thermomechanical stress affecting them during calendering. Thus, different demands are made on the calender and the process at the different stages of the treatment of the web, and it is of advantage to use a different method of calendering at the precalendering stage than is used for the
15 final calendering after coating. Uncoated board mainly contains raw materials such as cellulose, hemicellulose and lignin, contained in wood or other fibrous raw material. These have the structure of polymers having markedly higher glass transition temperatures than the polymers contained in
20 the coating. On the other hand, the base board consists of crossing fibres which can hardly move at all in relation to each other, whereas the coating consists of binders and small particles which move relatively easily in relation to each other and on the base board when compared to fibres. Thus,
25 uncoated board requires longer treatment times and higher thermomechanical stress before permanent deformations of the fibres are achieved. The coating layer, on the other hand, moves fairly easily on the surface of the base board when compared to fibres, and thus, shorter treatment times can be
30 used when processing the surface of coated board.

In the process of the invention for manufacturing coated board or paper, the web is finished by calendering at least such that the calendering which takes place prior to the
35 coating step, i.e. the so called pre-calendering, is

performed in a long-nip calender where the web is taken to a pressing zone formed by the belt and the backing roll, the fibres forming said web being subjected to a treatment in said zone during which the pressure in the treatment zone rises to 15 MPa at the most and the temperature of the web surface part reaches at least the glass transition temperature of the cellulose fibres.

The maximum pressure in the treatment zone is kept at 0 to 15 MPa, preferably, however, at 4 to 12 MPa. The web is taken to the treatment zone at a moisture content and temperature where at least the glass transition temperature of the material forming its surface part has been reached, the web thus having good workability properties. The glass transition temperature can be reached either by taking the web to the calendering by means of a pretreatment, such as steaming and/or wetting with water, or the conditions in the calendering zone are adjusted such that the preconditions for working the web are met in the calendering zone. Here, it is possible to use e.g. the combination of prewetting and a heated backing roll.

Thus, the calendering zone is mainly characterized by being formed between the belt and the stop surface for calendering arranged opposite the belt, and in that a pressure affecting the web prevails inside the calendering zone, its intensity varying from 0 to 15 MPa. The lower limit of the pressure range is reached, for example, such that the calendering zone is formed between at least two belts stretched by belt guiding means, and a stop surface, and the upper limit e.g. by so called shoe calender technology. In addition, it is characteristic of the calendering zone that the dwell time of the web in the calendering zone is at least 3 ms, while, however, it is 40 ms at the most, which at web speeds of 400 to 1000 m/min corresponds to calendering zone lengths of 50

to 270 mm.

A web thus precalendered, then, is characterized by good surface smoothness while its flexural strength remains almost at its initial level. When the web surface is smooth and sealed prior to the coating step, the amount of coating mix applied can be essentially reduced or, correspondingly, the printability of the end product can be improved, even to a level exceeding that described in WO 96/28609 without losing the flexural strength or "bulkiness" of the web.

In the case of a long-nip calender, the dwell time in the nip (the nip time) can be optimized without changing the other process conditions. In the present context, a long-nip calender is a machine having a nip length exceeding 50 mm. "Nip length" is the length over which the treated web is subjected to a pressing influence. Nip pressure may vary over the length of the nip e.g. such that the nip is divided e.g. by dividing the pressing shoe into sectors in the travelling direction of the web, the press power of the sectors towards the backing roll being independently controllable. Such a construction also makes it possible to alter the nip length stepwise by removing the press power of the outermost sectors. Nip length is selected according to the desired calendering effect. In the solution of the present invention, an uncoated paper or board web is treated with a calender having a nip length of 50 to 270 mm. When applying a speed of 800 to 1000 m/min, common in board manufacture, a nip time of 3 to 20 ms is thus obtained.

In the case of belt calenders, on the other hand, markedly greater forces in the surface direction have been found to occur than is the case for softcalenders. Thus, they will provide an advantageous effect on quality especially in the manufacture of coated board and corresponding products,

whereby the aim during the final calendering step is to move the coating mix on the surface of the base web and to align the coating mix particles. Such alignment is achieved by means of a belt calender supported by a backing roll or by a shoe calender having a very short shoe. The length of the shoe should not exceed 50 mm.

The result of the calendering can also be affected by the material of the backing roll, in other words, by using a soft or a hard backing roll. The material of the backing roll is selected in accordance with the type of nip, the belt material, and the requirements set by the manufactured product. The invention can be applied to both on-line and off-line machines.

Usually, board and paper are coated in the same fashion on both sides, but e.g. when manufacturing packing board, it may be necessary to coat only one side of the web or to prepare a different coat for each side of the web. In such a case it is possible to perform the calendering differently for the different sides of the web. Usually, heated rolls are used in calendering in order to produce a thermomechanical impact, but in some cases even cold rolls may be used at least for treating one of the sides of the web. An advantage provided by shoe calenders is that the web may be taken to the calender in a considerably wet state. This is beneficial particularly in on-line machines.

Claims:

1. A method for calendering paper and board when manufacturing coated grades of paper or board, comprising

- calendering at least one of the surfaces of an uncoated base material web,

- applying at least one layer of coating at least onto the calendered surface of the base web, and

- calendering at least the coated surface of the base web,

characterized by

- calendering the uncoated surface of the base web by means of a shoe calender having a nip length of at least 50 mm, and

- calendering the coated surface of the base web by means of a calender having a nip length of 50 mm at the most.

2. The method of claim 1, characterized by calendering the uncoated surface of the base web by means of a shoe calender having a nip length of 50 to 270 mm.

3. The method of claim 1, characterized by calendering the coated surface of the base web by means of a belt calender whose nip is formed between two rolls.

4. The method of claim 1, characterized by calendering the coated surface of the base web by means of a belt calender whose nip is formed by means of a short shoe.

5 5. The method of any one of the previous claims,
characterized by calendering the uncoated surface of the base
web by means of a shoe calender whose shoe is divided into
sectors in the travelling direction of the web, the
compression load of the sectors being independently
controllable.

10 6. The method of claim 2, characterized in that the maximum
pressure in the treatment zone is 0 to 15 MPa, preferably 4
to 12 MPa.

15 7. The method of claim 1 or 6, characterized by taking the
web to the first calender in a state in which the glass
transition temperature of at least its surface fibres has
been reached.

20 8. The method of claim 7, characterized by bringing the web
to glass transition temperature by the aid of prewetting or
presteaming, or the conditions in the calender zone, such as
the temperature of the backing roll and prewetting.

25 9. An arrangement for calendering paper and board in the
manufacture of coated grades of paper or board, the
arrangement comprising

- at least one first calender for treating at least
one of the surfaces of an uncoated base material
web,

30 - means for treating at least the calendered surface
of the base web with at least one coating mix layer,
and

35 - at least one second calender for treating at least
the coated surface of the base web,

characterized in that

- the first calender is a shoe calender having a nip length of at least 50 mm, and

- the second calender is a calender having a nip length of 50 mm at the most.

10. The arrangement of claim 9, characterized in that the first calender is a shoe calender having a nip length of 50 to 270 mm.

11. The arrangement of claim 9, characterized in that the second calender is a belt calender where the nip is formed between two rolls.

12. The arrangement of claim 9, characterized in that the second calender is a belt calender in which the nip is formed by means of a short shoe.

13. The arrangement of any one of the previous claims 9 to 12, characterized in that the first calender is a shoe calender whose shoe is divided into sectors in the travelling direction of the web, the compression load of the sectors being independently controllable.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/FI 99/00563

A. CLASSIFICATION OF SUBJECT MATTER

IPC6: D21G 1/00, D21H 19/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC6: D21G, D21H

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

FULLTEXT, WPI, EDOC

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 9628609 A1 (KORSNÄS AB), 19 Sept 1996 (19.09.96), page 2, line 11 - line 28; page 3, line 17 - line 25; page 5, line 8 - line 18, page 6, line 11 - line 12; page 6, line 30 - line 32; claims 1,9,11, 13 --	1-13
A	US 5163364 A (ALFRED BUBIK ET AL), 17 November 1992 (17.11.92) --	1-13
A	US 5582689 A (ROLF VAN HAAG ET AL), 10 December 1996 (10.12.96), abstract --	1-13

☒ Further documents are listed in the continuation of Box C.☒ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

18 October 1999

Date of mailing of the international search report

21-10-1999

Name and mailing address of the ISA/
Swedish Patent Office
Box 5055, S-102 42 STOCKHOLM
Facsimile No. +46 8 666 02 86

Authorized officer

Helena Hemphälä/MP
Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT

International application No.

PCT/FI 99/00563

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5483873 A (PEKKA KOIVUKUNNAS ET AL), 16 January 1996 (16.01.96), abstract --	1-13
A	WO 9534715 A1 (ALBANY NORDISKAFILT AB), 21 December 1995 (21.12.95), page 3, line 4 - line 21, claim 6 --	1-13
A	WO 9713035 A1 (VALMET CORPORATION), 10 April 1997 (10.04.97), page 16 - page 17, figures -----	1-13

INTERNATIONAL SEARCH REPORT
Information on patent family members

International application No.
PCT/FI 99/00563

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9628609 A1	19/09/96	AU 3358595 A	14/03/96
		AU 4959596 A	02/10/96
		CA 2214977 A	19/09/96
		EP 0804116 A	05/11/97
		EP 0815319 A	07/01/98
		FI 960453 A	17/09/96
		JP 11501994 T	16/02/99
		SE 503580 C	08/07/96
		SE 9500949 A	08/07/96
US 5163364 A	17/11/92	AT 76134 T	15/05/92
		DE 3920204 A,C	10/05/90
		EP 0370185 A,B	30/05/90
		SE 0370185 T3	
US 5582689 A	10/12/96	AT 154651 T	15/07/97
		CA 2144252 A	25/09/95
		DE 4410129 A	28/09/95
		DE 59500323 D	00/00/00
		EP 0675224 A,B	04/10/95
		FI 951299 A	25/09/95
		JP 8003888 A	09/01/96
US 5483873 A	16/01/96	CA 2116298 A	09/09/94
		DE 69405621 D,T	19/02/98
		EP 0617165 A,B	28/09/94
		SE 0617165 T3	
		FI 95061 B,C	31/08/95
		FI 931021 A	09/09/94
		JP 6306791 A	01/11/94
WO 9534715 A1	21/12/95	AU 678324 B	22/05/97
		AU 2756495 A	05/01/96
		BR 9508701 A	12/08/97
		CN 1150830 A	28/05/97
		EP 0767851 A,B	16/04/97
		FI 964973 A	12/12/96
		JP 10501852 T	17/02/98
		NO 965266 A	16/12/96
		NZ 288369 A	19/12/97
		SE 502960 C	26/02/96
		SE 9402094 A	16/12/95
		US 5836242 A	17/11/98
		ZA 9504985 A	14/02/96
WO 9713035 A1	10/04/97	AU 7133496 A	28/04/97
		AU 7133596 A	28/04/97
		CA 2233900 A	10/04/97
		EP 0856084 A	05/08/98
		EP 0856085 A	05/08/98
		FI 954745 A	06/04/97
		WO 9713036 A	10/04/97